




DirectTex® Blackout VI

Fields of application

.02 .04 .05 .07 .08

Specifications

	512335 009
	100 % polyester weave fabrics PVC-free, recyclable
	ca. 155/ 252/ 310/ 505 cm ca. 61/ 99/ 122/ 199 inch other widths available on request
	B-s1, d0 DIN EN 13501-1
	ca. 330 g/m ² ca. 9.7 oz/yd ²
	ca. 0.46 mm ca. 460 µm
	rolls 50 m 55 yd
	warp: 161.6 N weft: 55.0 N DIN EN ISO 9073-4
	white (front): 5 black (back): 6 DIN EN ISO 105-B02
	white (front): 89.8 black (back): 39.2 DIN 5033-1
	ultrasonic cut
	blackout

	100 Pa: 21.1 l/(m ² s) 200 Pa: 41.0 l/(m ² s) DIN EN ISO 9237
	white (front): 0.8 % black (back): 0.6 % DIN EN 410
	white (front): 0.0 % black (back): 0.0 % DIN EN 410

Printing methods

print	UV	Latex	Dyesub
Inside	•	•	•
Outside			

Article shrinkage (50 sec hold up time)

	shrinkage in cross direction	shrinkage in longitudinal direction	recommended fixing temperature
180°C	0,8 %	1,1 %	•
190°C	1,2 %	1,7 %	
200°C	1,6 %	1,9 %	
210°C	2,4 %	2,6 %	

Certifications



DirectTex® Blackout VI

Fields of application

.02 .04 .05 .07 .08



Ref.-Nr.: 512335 009 | Preview print sample