

















DirectTex® Stretch Twill Soft

Fields of application

.02 .04 .05 .06 .07

Specifications

	REF. 584097 123
	100 % polyester weave fabrics PVC-free, recyclable
	ca. 155/ 252/ 310 cm ca. 61/ 99/ 122 inch other widths available on request
	B-s1, d0 DIN EN 13501-1 M1 NF P 92 503
	ca. 120 g/m ² ca. 3.5 oz/yd ²
	ca. 0.22 mm ca. 220 µm
	rolls 50/ 100 m 55/ 109 yd
	blank: 26.9 % DIN EN 410
	blank: 0.1 % DIN EN 410
	blank: 7 DIN EN ISO 105-B02
	warp: 1.1 % weft: 10.3 % DIN EN 14704-1
	indirect light
	heat, ultrasonic cut

	warp: 20.3 N weft: 22.5 N DIN EN ISO 13937-2
	warp: 1242.4 N weft: 740.7 N DIN EN ISO 13934-1
	warp: 33.3 % weft: 39.6 % DIN EN ISO 13934-1

Printing methods

print	UV	Latex	Dyesub
Inside	•		•
Outside	•		•

Article shrinkage (50 sec hold up time)

	shrinkage in cross direction	shrinkage in longitudinal direction	recommended fixing temperature
180°C	-3,0 %	0,3 %	•
190°C	1,0 %	-4,3 %	
200°C	1,1 %	-1,3 %	
210°C	1,2 %	-0,5 %	

Certifications





DirectTex® Stretch Twill Soft

Fields of application

.02 .04 .05 .06 .07



Ref.-Nr.: 584097 123 | Preview print sample



PONGS Technical Textiles GmbH
Bahnhofstraße 21 Phone +49 36645 350-0
07919 Pausa-Mühltrorf salestt@pongs.de
Germany www.pongs.com

Find the latest version by scanning the QR code.
We reserve the right for technical modifications.
The above mentioned details are non-binding.
A tolerance of $\pm 5\%$ is valid. Effective: 2021/02