

# DirectTex® Softimage Elastico®

Fields of application

**.02 .04 .05 .06 .07**

## Specifications



599190 129



100 % polyester  
knit fabrics  
PVC-free, recyclable



ca. 160/ 252/ 320 cm  
ca. 63/ 99/ 126 inch  
other widths available on request



B-s1, d0 DIN EN 13501-1  
M1 NF P 92 503 - 507  
NFPA 701



ca. 175 g/m<sup>2</sup>  
ca. 5.2 oz/yd<sup>2</sup>



ca. 0.55 mm  
ca. 550 µm



rolls  
50/ 100 m  
55/ 109 yd



blank: 6  
DIN EN ISO 105-B02



warp: 2.8 % / 12.6 %\*  
weft 13.3 % / 10.9 %\*  
DIN EN 14704-1



crease-resistant, stretchable



cold, ultrasonic cut



warp: 493 N / 427 N\*  
weft: 845 N / 964 N\*  
DIN EN ISO 13934-1 - max. tensile strength



warp: 42.7 % / 55.8 %\*  
weft: 90.5 % / 79.0 %\*  
DIN EN ISO 13934-1 - max. tensile elongation



warp: 29.9 N / 40.3 N\*  
weft: 34.4 N / 32.3 N\*  
DIN EN ISO 13937-2 - trouser tear propagation

## Printing methods

print	UV	Latex	Dyesub
Inside	•		•
Outside			

## Article shrinkage

(50 sec hold up time)

	shrinkage in cross direction	shrinkage in longitudinal direction	recommended fixing temperature
180°C	0,5 %	0,0 %	
190°C	0,5 %	0,5 %	•
200°C	0,5 %	0,8 %	
210°C	0,6 %	1,2 %	

## Certifications



\* only for 252 cm (100 inch) width



## DirectTex® Softimage Elastico

Fields of application

**.02 .04 .05 .06 .07**



Ref.-Nr.: 599190 129 | Preview print sample



**PONGS Technical Textiles GmbH**  
Bahnhofstraße 21 Phone +49 36645 350-0  
07919 Pausa-Mühltrorf salestt@pongs.de  
Germany www.pongs.com

Find the latest version by scanning the QR code.  
We reserve the right for technical modifications.  
The above mentioned details are non-binding.  
A tolerance of  $\pm 5\%$  is valid. Effective: 2021/02