

PrintTex® SUNTEX® II

Fields of application

.02 .05 .07 .08

Specifications



550321 094



100 % Trevira CS
weave fabrics
PVC-free, recyclable



505 cm
199 inch
other widths available on request



ca. 342 g/m²
ca. 10.1 oz/yd²



ca. 0.4 mm
ca. 400 µm



rolls
50 m
55 yd



blank: 6-7
DIN EN ISO 105-B02



blank: 23.5 %
DIN EN 410



blank: 1.1 %
DIN EN 410



blank: 93.13
DIN 5033-1



trapezoid tear resistance
warp: 1122.5 N weft: 169.5 N
DIN EN ISO 9073-4



maximum tensile strength
warp: 3586.0 N weft: 853.6 N
DIN EN ISO 13934-1



maximum tensile elongation
warp: 59.4 % weft: 35.8 %
DIN EN ISO 13934-1



heat, ultrasonic cut

water repellency
blank: 5
DIN EN ISO 4920

water absorption
blank: 16.7 %
DIN EN 29865 (Bundesmann)

lotus effect (after 10 min)
blank: 1-2
DIN EN 29865 (Bundesmann)

water throughput
blank: 96.3 ml
DIN EN 29865 (Bundesmann)

oil repellent properties
blank: 6
AATCC 118-1997

resistance to water
blank: 10.2 mbar
DIN EN 20811

Printing methods

print	UV	Latex	Dyesub
Inside	•		
Outside	•		

Certifications



PrintTex® SUNTEX® II

Fields of application

.02 .05 .07 .08



Ref.-Nr.: 550321 094 | Preview print sample