

PrintTex® SUNTEX® I

Fields of application

.02 .05 .07 .08

Specifications



564255 094



100 % Trevira CS
weave fabrics
PVC-free, recyclable



505 cm
199 inch
other widths available on request



ca. 245 g/m²
ca. 7.2 oz/yd²



ca. 0.4 mm
ca. 400 µm



rolls
50 m
55 yd



blank: 7
DIN EN ISO 105-B02



blank: 26.6 %
DIN EN 410



blank: 1.4 %
DIN EN 410



blank: 94.47
DIN 5033-1



trapezoid tear resistance
warp: 380.1 N weft: 184.7 N
DIN EN ISO 9073-4



maximum tensile strength
warp: 1991.3 N weft: 2135.3 N
DIN EN ISO 13934-1



maximum tensile elongation
warp: 56.0 % weft: 36.2 %
DIN EN ISO 13934-1



heat, ultrasonic cut

water repellency
blank: 5
DIN EN ISO 4920

water absorption
blank: 9.3 %
DIN EN 29865 (Bundesmann)

lotus effect (after 10 min)
blank: 1-2
DIN EN 29865 (Bundesmann)

water throughput
blank: 8.6 ml
DIN EN 29865 (Bundesmann)

oil repellent properties
blank: 6
AATCC 118-1997

resistance to water
blank: 25.2 mbar
DIN EN 20811

Printing methods

print	UV	Latex	Dyesub
Inside	•		
Outside	•		

Certifications



PrintTex® SUNTEX® I

Fields of application

.02 .05 .07 .08



Ref.-Nr.: 564255 094 | Preview print sample